



# SEALTEK PTY LTD

## ADVANCED COATING TECHNOLOGIES

44 Sophia Street, Fairlands, Johannesburg  
 P.O. BOX 731 074, Fairlands 2030, South Africa  
 TELEPHONE: + 27 10 594 - 4726  
 E-mail: info@sealtek.co.za  
 Reg no: 2015/358427/07

### SPEC SHEETS - DAMPEND

DampEnd is a two-part system consisting of dry and wet ingredients that gets mixed together. DampEnd is a waterproofing system that has been specifically designed for damp proofing. All the binders and materials that DampEnd comprises of is eco-friendly.

Surface Preparation	<ul style="list-style-type: none"> <li>• Ensure that the Substrate has been washed off and is free of any dust or any objects and chemicals that might cause non-adhesion to the substrate.</li> <li>• Ensure that the substrate has dried properly before any application of the product.</li> <li>• It is recommended that a primer (AquaPel) is applied to the substrate before applying the DampEnd.</li> </ul>
Method of Application	<ul style="list-style-type: none"> <li>• DampEnd is pre-packaged in a 20ltr bucket of dry mix and a 20ltr pre-mixed wet mix – All additives have been pre-mixed in the dry mix content, but it is recommended that it is turned over on site before adding any liquid.</li> <li>• Open the bucket of mixtures and gradually add the dry mix to the wet mix while continuously turning over the combination.</li> <li>• Ensure the substrate has been properly prepared as above.</li> <li>• Cover all surrounding areas with masking tape to avoid damage or overspill.</li> <li>• A Block Brush can be used to apply the mixture to the substrate. Once the 1<sup>st</sup> coat has been applied the surface must be touch dry before the 2<sup>nd</sup> and 3<sup>rd</sup> coat is applied. After application the area needs to cure.</li> </ul>
Practical Coverage	<ul style="list-style-type: none"> <li>• 15-30m<sup>2</sup> per 23kg kit at 2-3coats</li> </ul>
Cleaning	<ul style="list-style-type: none"> <li>• Clean the Brushes immediately after use, with water, as it will be very difficult to clean once the mixture has dried.</li> </ul>
Drying Time	<ul style="list-style-type: none"> <li>• Touch Dry 1-2 Hours at ± 25 °C</li> <li>• Fully Cured - 7 Days at ± 25 °C</li> </ul>
Colours	<ul style="list-style-type: none"> <li>• The DampEnd can be done in a Cement Grey</li> </ul>
Product Data:	
VOC:	<ul style="list-style-type: none"> <li>• Low VOC's &lt; 1%</li> </ul>
FlashPoint	<ul style="list-style-type: none"> <li>• Non-Flammable</li> </ul>
Solid Content	<ul style="list-style-type: none"> <li>• &gt;75%</li> </ul>
Characteristics	<ul style="list-style-type: none"> <li>• Flexible</li> <li>• UV Stable</li> <li>• Exceptional Adhesion Properties</li> </ul>

<b>Safety Data</b>	
Eye Contact	<ul style="list-style-type: none"><li>• If in eyes wash out immediately with water. Might cause eye irritation as a precaution seek medical advice</li><li>• No harmful effect expected, do remove victim to a well-ventilated area as precaution.</li><li>• Rinse mouth with water, seek medical advice.</li><li>• Skin might feel dry if in contact for long duration of time.</li><li>• This product has low Toxicity, material has been classified as non-hazardous</li></ul>
Inhalation	
Ingestion	
Skin Contact	
Toxicology	
<b>Ecological Info</b>	<ul style="list-style-type: none"><li>• 100% Eco Friendly</li><li>• Non-Environmentally Hazardous</li></ul>
<b>Storage</b>	<ul style="list-style-type: none"><li>• 6months at 25°C. Store in cool dry conditions</li></ul>

